

Multi Construction Chemicals (PTY)LTD

Tel: (011) 864 4654/5 | Fax: (011) 864 4406 / 908 5336

Email : mcc@mccsa.co.za

www.mccsa.co.za



Reg. No : 1986/002014/07

9 Vereeniging Road, Alrode 1449
PO Box 124138, Alrode 1451, South Africa
Reg. No : 1986/002014/07

MULTIPOXY 1308 Epoxy Enamel Coating

Description

MULTIPOXY 1308 a decorative and protective epoxy paint which provides both a high gloss finish and a tough chemical resistant easily cleaned surface.

Typical Applications

Coating of floors, concrete surfaces, machinery, pipes, ablution blocks, showroom floors, hospitals, schools, etc.

Advantages

- * Long pot life
- * High coverage
- * Ease of application
- * Tough and chemical resistant
- * Good resistance to dry heat
- * Available in a variety of colours.

Composition

Twin pack epoxy enamel

Typical Properties

Mix Ratio:	As supplied
Spreading Rate:	4 - 8m ² / litre per coat depending on surface conditions
Pot Life:	1 hour
Drying time:	Touch dry: 4 hours
Hard dry:	8 hours
Full Cure:	7 days
Dry heat:	120°C
Wet heat:	60°C
Flashpoint:	17°C
Application temp:	10°C to 30°C

Directions for Use

- * Mix thoroughly in the proportions supplied.
- * Allow to stand for 20 minutes before application.
- * Apply to suitably prepared and primed surfaces.
- * The second coat should be applied between 8 to 24 hours after application of first coat.
- * Application is by brush, roller or spray.
- * Non-skid surfaces may be achieved by sprinkling a fine silica grit onto the first coat while still wet.

Watchpoints

- * This material is not suitable for exterior use.
- * Apply only in well ventilated areas.
- * Keep away from naked flame.
- * Wear protective clothing and in case of eye contact wash well with clean water and obtain medical assistance immediately.

Packaging

Supplied in 1, 2, 5, 10 and 25 litre kits.

Quality Assurance

MULTI CONSTRUCTION CHEMICALS (PTY) LTD's production and testing programmes comply to local testing standards.