


# Multi Construction Chemicals (PTY)LTD

Tel: (011) 864 4654/5 | Fax: (011) 864 4406 / 908 5336

Email : [mcc@mccsa.co.za](mailto:mcc@mccsa.co.za)

[www.mccsa.co.za](http://www.mccsa.co.za)



Reg. No : 1986/002014/07

9 Vereeniging Road, Alrode 1449  
PO Box 124138, Alrode 1451, South Africa  
Reg. No : 1986/002014/07

## MULTIPRIME 1308 Epoxy Primer

### Description

MULTIPRIME 1308 epoxy primer / sealer for application to porous and friable surfaces and used in conjunction with MULTISEAL Polyurethane and Polysulphide joint sealants.

### Typical Applications

An adhesion promoter between MULTISEAL Polyurethane and Polysulphide sealants for a large variety of substrates, i.e. masonry, steel, glass, ceramics, and concrete, etc. Multiprime 1308 must be used when sealing joints in water retaining structures.

### Advantages

- \* Long pot life
- \* Easy application
- \* Good penetration

### Composition

Twin pack epoxy priming system

### Typical Properties

Mix ratio:	As supplied
Spreading rate:	4 - 8 m <sup>2</sup> per litre
Pot life:	1 hour
Drying time:	Touch dry: 4 hrs, Hard dry: 8 hrs.
Dry heat:	120°C
Wet heat:	60°C
Application temp:	10°C to 30°C

### Directions for Use

Mix thoroughly and brush apply to clean, dry surfaces.

### Watchpoints

Apply only in well ventilated areas. Keep away from naked flame. Wear protective clothing and in case of eye contact, wash well with clean water and obtain medical assistance immediately.

### Packaging

Supplied in 1 and 2 litre kits

### Quality Assurance

MULTI CONSTRUCTION CHEMICALS (PTY) LTD's production and testing programmes comply with all local and international testing standards.