

Masonry Cement Composites (Pty) Ltd

Registration Number: 2014/263264/07

VAT No: 4090268972

27 Reuben Kaye Road, Parow Industrial, 7493

Tel: 021-934 0374 / Whatsapp: 068 006 4419

Generated on: 2026-09-20 17:13:13

UV Sealer Clear 5Lt



SKU: MWUVC

TECHNICAL DATASHEET

UV SEALER

Solvent Based Thin Film Polyurethane Sealer

UV SEALER is a solvent based thin film polyurethane sealer for use on walls and floors where a high chemical resistance, abrasion resistance, stain resistance and non-yellowing sealing is required. Hard curing and long lasting, this sealer will adhere to all concrete, brick, tiles and previously coated surfaces. Available in clear and colours.

TYPICAL APPLICATION

For sealing over indoor and outdoor surfaces where high abrasion resistance, chemical resistance and UV stability is required.

ADVANTAGES

- Ease of application
- Excellent coverage
- Early hard set
- High chemical resistance
- High abrasion resistance

- High stain resistance
- High flexibility
- Gloss / Satin / Matt finish
- Moisture tolerant
- Fast cure

WATCH POINTS

- Apply in well-ventilated areas.
- Do not expose the coated surface to moisture for 24 hours
- Ensure rollers are dry before use
- Clean spills or splatters as soon as noticeable with thinners while the product is still liquid.
- Do not dilute with acetone, use only xylene.

DIRECTIONS FOR USE

Surface Preparation:

Surfaces to be clean, sound and free of deleterious substances. Remove all laitance, oil, grease, paints, mould oil or curing compound from surfaces using wire brush, bush hammer, scabbler or other plant as appropriate. Previously coated surfaces will need to be well abraded or stripped of the coatings if not securely bonded. Dense, sealed surfaces will need to be grinded open to create a mechanical profile.

Priming:

No priming is required. An acrylic primer can be used to seal up porous surfaces such as COLOUR RETAINER and prevent unnecessary draw in of the first few coats on application. As well as provide a more even and consistent finish.

Application:

Mix by hand and do not aerate the mix especially if a mechanical mixer is used. Mix the resin and hardener together in a clean bucket or metal drum. Roll out with a dry mohair roller, being careful to pick up roller lines and ends where these build up and allow to settle. Allow 1-2 hours between coats. Two coats are recommended for optimum sealing and protection. Allow 24 hours without exposure to surface moisture to prevent discolouration then open to light traffic.

TYPICAL PROPERTIES

Yield 5 Litre kits

Coverage 1st coat 8-10 m² per litre

Coverage 2nd coat 15 m² per litre

Application Temperature 10°C to 25 °C

Application Roll on application

Finish High Gloss

Dry film Thickness 80-100 micron

Overcoat Time 1-2 hours

Pot Life 30 minutes

Cure: Light Traffic 12 hours

Cure: Heavy Traffic 48 hours

Cleaning Thinners

Equipment Care

All tools should be cleaned with thinners immediately after use. If delayed, equipment will need mechanical action to clean or be discarded.

Warranty

Masonry Cement Composites (PTY) Ltd products have a manufacturing defect free warranty. Products, when applied as stipulated in this technical datasheet, will perform as specified without manufacturing defect.

REVISION: 5.2