

Masonry Cement Composites (Pty) Ltd

Registration Number: 2014/263264/07

VAT No: 4090268972

27 Reuben Kaye Road, Parow Industrial, 7493

Tel: 021-934 0374 / Whatsapp: 068 006 4419

Generated on: 2026-08-09 14:24:13

Poxy Crack Injection



SKU: MWP1306

TECHNICAL DATASHEET

POXY CRACK INJECTION

Crack Injection Epoxy

POXY CRACK INJECTION is a high strength, low viscosity pourable epoxy compound used to fill tight gaps and cracks in concrete. Sets at low temperatures and is resistant to moisture and has excellent chemical resistance.

TYPICAL APPLICATION

Provides structural repairs to cracks and damaged concrete structures such as columns, beams, floors, and bridge decks. May be used as a casting and encapsulation compound.

ADVANTAGES

- Low viscosity
- Long pot life
- Self-Leveling
- High compressive strength

- Excellent adhesion to concrete
- Non-shrink
- Moisture tolerant
- High resistance to water and chemicals

WATCH POINTS

- Exposure of the epoxy to intense lighting or direct sunlight will produce discolouration in time
- Do not hold a full kit in a bucket for more than 5 minutes, rather pour out onto the target areas and work within the working time of the product.

DIRECTIONS FOR USE

Surface Preparation:

Surfaces to be clean, sound and free of deleterious substances. Remove all laitance, oil, grease, paints, mould oil or curing compound from surfaces using wire brush, bush hammer, scabbler or other plant as appropriate.

Priming:

No priming is required.

Application:

Mix the resin and hardener together in a clean bucket. Mix only enough to be able to work out within the pot life of the epoxy. Pour out using dispenser, gun or pump into confined spaces. Allow 8 hours before applying pressure or loads on the repaired areas. Overcoat with any solvent free epoxy-based coating such as POXY 1938 in colour of choice within 12 hours to ensure good chemical bond with the coating.

TYPICAL PROPERTIES

Appearance Clear amber liquid

Application Temp 10°C to 25 °C

Compressive Strength >50MPa

Pot Life 30 minutes

Initial set 1-2 hours

Practical Cure 4-5 hours

Full Cure: 5 days 5 Days

Chemical Resistance Resists aggressive cleaning materials, acids, alkalis and water solutions

Bond Strength 1,5 N/mm²

Cleaning Thinners

Equipment Care

All tools should be cleaned with thinners immediately after use. If delayed, equipment will need thinners or mechanical action to clean or be discarded.

Masonry Cement Composites (PTY) Ltd products have a manufacturing defect free warranty. Products, when applied as stipulated in this technical datasheet, will perform as specified without manufacturing defect.

REVISION: 5.2