

Masonry Cement Composites (Pty) Ltd

Registration Number: 2014/263264/07

VAT No: 4090268972

27 Reuben Kaye Road, Parow Industrial, 7493

Tel: 021-934 0374 / Whatsapp: 068 006 4419

Generated on: 2026-07-15 04:06:53

Hyseal 211 Flex Cement Slurry 23Kg



SKU: MWMH2110

TECHNICAL DATASHEET

HYSEAL 211

Cementitious Waterproofing Slurry

HYSEAL 211 is two-part waterproofing cementitious slurry with a high polymer content. High adhesion and water-resistant properties allow application to almost any surface. It seals concrete surfaces through moisture absorption, blocking the pores to prevent water penetration. Providing positive and negative waterproofing against dampness and ground water, as well as hydrostatic pressure.

TYPICAL APPLICATION

A slurry application for waterproofing sewage tanks, reservoirs and pools, shower walls and bases, balconies, pre-stressed concrete slabs.

ADVANTAGES

- Excellent adhesion
- High bond strength
- Improved impact resistance
- Easy application
- Waterproofing
- Non-toxic

WATCH POINTS

- Surfaces need to be able to dry out
- Do not add more water to the mix once initial set occurs
- Water addition must be checked on site for placement consistency
- Allow 5 days before exposing the slurry to extended water submersion.

DIRECTIONS FOR USE

Surface Preparation:

Surfaces are to be clean, sound and free of deleterious substances. Remove all laitance, oil, grease, mould oil or curing compound from concrete surfaces using wire brush, bush hammer, scabbler or other plant as appropriate. When repairing damaged concrete, ensure that all loose concrete has removed down to a firm base. Repair with PLAST 1038 or GROUT CEM 60. Surfaces can be damp but not continually wetting out or bleeding water.

Priming:

No priming is required. Dry surfaces are to be wetted with water and remain damp during application of the HYSEAL 211.

Application:

Mix 20Kg HYSEAL (Powder) to 3Lts supplied white polymer liquid in a bucket using a mechanical mixer. Add additional 4 litres water MAXIMUM to obtain a slurry consistency. Less water can be added to obtain a thicker slurry mix. Ensure all lumps have been broken up and apply using a block brush or sprayer over surfaces. Use within 20 minutes of mixing with continuous agitation during application. DO NOT ADD MORE WATER to reconstitute the mix, rather discard the mix and make fresh. Apply with a sprayer or block brush or at a rate of 1mm thickness in one directional strokes (e.g. horizontally). Allow to cure for 12 hours between coats. Apply a second at right angles to the first one (e.g. vertically). A third coat maybe applied at right angles to the second coat (e.g. horizontally) after 12 hours where a high degree of certainty is required for waterproofing capabilities with a target thickness is 3mm. Once complete, keep exposed surfaces of the HYSEAL 211 damped down for 2-3 days using mist spray or using concrete curing compound to guard against premature dehydration of the slurry.

TYPICAL PROPERTIES

Equipment Care

Appearance Grey

Coverage 16m² per kit

Finish Textured

Working Time 20 Minutes

Initial Set Time 30 Minutes

Hard Set Time 4 Hours

Overcoat Time 12 Hours

Application Temp. 15°C to 25 °C

Full Flex 3 Days

Waterproof Cure 5 Days

Application Thickness 1mm per coat

Target Thickness 3mm (3 coats)

Compressive Strength 15 MPa (1 day)

25 MPa (28 days)

Yield per Kit 16 Litres

Water Required 4 Litres

Water Resistance (28 Days Full Cure) Negative – 3 Bar

Positive – 5 Bar

All tools should be cleaned with water immediately after use. If delayed, the equipment will need mechanical action to clean or be discarded.

Warranty

Masonry Cement Composites (PTY) Ltd products have a manufacturing defect free warranty. Products, when applied as stipulated in this technical datasheet, will perform as specified without manufacturing defect.

REVISION: 5.2