

Masonry Cement Composites (Pty) Ltd

Registration Number: 2014/263264/07

VAT No: 4090268972

27 Reuben Kaye Road, Parow Industrial, 7493

Tel: 021-934 0374 / Whatsapp: 068 006 4419

Generated on: 2026-08-25 04:08:31

Hyrez Mortar 20Lt



SKU: MWPUMTK1

TECHNICAL DATASHEET

HYREZ MORTAR

Three Component Polyurethane Mortar Mix

HYREZ MORTAR is a polyurethane mortar mix that is used primarily to fill and raise horizontal surfaces or voids. Fine, hard aggregate makes the mortar high in strength and can be used on uneven areas with good adhesion to concrete. Water washable and textured finishing. Sets at low temperatures and is resistant to chemicals and has excellent chemical resistance.

TYPICAL APPLICATION

For use on commercial and industrial flooring and void filling applications where the mix can be compacted in. Long lasting, water resistant, chemical resistant mortar. Used on bridge decks, concrete structures, bearing pads and joint stops.

ADVANTAGES

- Hard wearing
- Long lasting
- Rapid hardening
- Textured finishing
- Water washable
- Compacting mix application
- Neutral sand colour
- High resistance to water and chemicals
- Easy to maintain
- Noncracking
- Abrasion and impact resistant

WATCH POINTS

- Exposure of the mortar to intense lighting or direct sunlight will produce discolouration in time
- Do not hold a full kit in a bucket for long period of time while mixed, rather empty and spread out onto substrate within the working time of the product.
- Mortar maybe textured if resin is not worked to the surface by floating with a steel trowel

DIRECTIONS FOR USE

Surface Preparation:

Surfaces to be clean, sound and free of deleterious substances. Remove all laitance, oil, grease, paints, mould oil or curing compound from surfaces using wire brush, bush hammer, scabbler or other plant as appropriate.

Priming:

HYREZ PRIMER: Mix Part A (Resin) and Part B (Hardener) and then Part C until a smooth mortar. Trowel or roll out over the substrate surface, working into the substrate where possible.

Application:

Mix the resin and hardener together in a clean bucket and mix in the aggregate. Mix only enough to be able to spread and trowel out within the pot life of the product. Trowel out into wet or tacky primer using trowels or straight edge over horizontal surfaces, and compact into place to remove trapped air. Smooth off with a steel trowel, wiping down the face of the trowel with xylene to assist in compression gliding over the surface of the mortar. If filling voids, prime the inside of the void and then compact in the mortar mix. Smooth off with a steel trowel. Allow 8-12 hours before overcoating or opening to light traffic. Overcoat with any solvent free polyurethane or epoxy-based coating such as HYREZ UVR or POXY 1938 in colour of choice.

TYPICAL PROPERTIES

Yield 20 Litres

Coverage 2m² @10mm thick

Appearance Sand Colour Mortar

Application Temp 10°C to 25 °C

Mortar Thickness 5mm to 40mm

Pot Life 20 minutes

Overcoat Time 8-12 hours

Cure: Light Traffic 12 hours

Full Cure: 7 days 7 Days

Compressive Strength 70MPa

Bond Strength 3,5 N/mm²

Cleaning Solvent

Equipment Care

All tools should be cleaned with thinners immediately after use. If delayed, the equipment will need mechanical action to clean or be discarded.

Warranty

Masonry Cement Composites (PTY) Ltd products have a manufacturing defect free warranty. Products, when applied as stipulated in this technical datasheet, will perform as specified without manufacturing defect.

REVISION: 5.2