

Masonry Cement Composites (Pty) Ltd

Registration Number: 2014/263264/07

VAT No: 4090268972

27 Reuben Kaye Road, Parow Industrial, 7493

Tel: 021-934 0374 / Whatsapp: 068 006 4419

Generated on: 2026-10-13 02:02:22

Porefill 5Lt



SKU: MWWBCPF5

TECHNICAL DATASHEET

POREFILL

Acrylic Water Based UV Stable Porefill Paste

POREFILL is an acrylic water-based paste that is pigmented to the colour of the STONE CARPET colour choice and forms a translucent pigmented film over pores in STONE CARPET applications. Being UV stable, it can be used indoors or outdoors STONE CARPET has been applied. POREFILL closes gaps between the stones to allow for better cleanability.

TYPICAL APPLICATION

Applied over STONE CARPET applications in areas where a higher degree of cleanability is required for STONE CARPET installations. Aids in better water run-off in showers and bathrooms.

ADVANTAGES

- Closes gaps between stones
- UV stable

- Economical
- Easy to apply
- High flexibility
- Excellent adhesion to the stones

WATCH POINTS

- Take up excess product on the floor – do not allow to stand
- Only apply over the STONE CARPET once the binder has set hard
- Do not allow any moisture between the STONE CARPET before applying or after application for at least 24 hours or until the POREFILL has set hard.

DIRECTIONS FOR USE

Surface Preparation:

STONE CARPET installations need to be clean and completely dry.

Priming:

No priming is required.

Application:

Using a rubber squeegee, work the POREFILL paste directly into the pores of the STONE CARPET. Press POREFILL into the gaps and pick up excess product by rolling over the POREFILL with a clean, dry sponge roller as not to allow a thick layer over the exposed stones. Excess POREFILL will give the STONE CARPET a very plastic look and take away from the natural stone aesthetic. Allow to dry for 24 hours and if pores are still visible in some areas, spot applications of a second coat maybe required. Allow to dry for 24 hours or until the appearance of the POREFILL has become uniformly translucent.

TYPICAL PROPERTIES

Density 1.0g/cm³

Mixing Ratio Do not dilute

Appearance Pigmented paste

Application Temp. 10 - 25°C

Colour on Drying Clear

Coverage 1m²/litre

Equipment Care

Clean all equipment immediately after use with water.

Warranty

Masonry Cement Composites (PTY) Ltd products have a manufacturing defect free warranty. Products, when applied as stipulated in this technical datasheet, will perform as specified without manufacturing defect.

REVISION: 5.3