TECHNICAL DATA SHEET

KWA-ZULU NATAL

T: 031 701 2619
E: natal@mccsa.co.za
Unit 7, Marlmead, 4 Reed Place,
Maxmead, Pinetown, 3610

WESTERN CAPE

T: 021 934 0373
E: saleswc@mccsa.co.za
27 Reuben Kaye Rd, Parow Industrial,
7493 | P.O. Box 736, Brackenfell, 7561



MULTI CONSTRUCTION CHEMICALS

www.mccsa.co.za

MULTI POXY 1942

Two Component Colour Epoxy Tile Grout

Description

MULTI POXY 1942 is an epoxy grout that is available in a variety of colours and is used primarily as a tile grout. Fine, hard fillers make the grout long lasting and can be used in damp areas. Water washable and smooth finishing. Sets at low temperatures and is resistant to moisture, UV light and has excellent chemical resistance.

Typical Applications

For use in commercial and industrial applications where long lasting, water resistant, chemical resistant grouting is required. Used in showrooms, offices, kitchens, laboratories, pools, shopping areas, floors and domestic applications.

Advantages

- Good colour stability
- Long lasting
- Smooth finishing
- Water washable
- Easy application
- Superb aesthetic
- High resistance to water and chemicals
- Easy to maintain
- Noncracking
- · Variety of colours

Typical Properties

Yield	1 Litres
Coverage	Grout fill dependant
Application Temp	10°C to 25 °C
Grout Thickness	Unlimited
Pot Life	20 minutes
Cure: Light Traffic	24 hours
Full Cure: 7 days	7 Days
Compressive	60MPa
Strength	
Bond Strength	1,5 N/mm2
Cleaning	Water

Watch Points

- Colours must be from the same batch to reduce risk of colour variations
- Exposure of the coating to intense lighting or direct sunlight will produce discolouration in time
- Staining of unsealed tiles may occur on direct, sustained contact


TECHNICAL DATA SHEET

KWA-ZULU NATAL

T: 031 701 2619
E: natal@mccsa.co.za
Unit 7, Marlmead, 4 Reed Place,
Maxmead, Pinetown, 3610

WESTERN CAPE

T: 021 934 0373
E: saleswc@mccsa.co.za
27 Reuben Kaye Rd, Parow Industrial,
7493 | P.O. Box 736, Brackenfell, 7561



MULTI CONSTRUCTION CHEMICALS

www.mccsa.co.za

MULTI POXY 1942

Directions for Use

Surface Preparation:

Surfaces to be clean, sound and free of deleterious substances. Remove all laitance, oil, grease, paints, mould oil or curing compound from surfaces using wire brush, bush hammer, scabbler or other plant as appropriate.

Priming:

No priming is required.

Application:

Mix the resin and hardener together in a clean bucket. Mix only enough to be able to grout within the pot life of the epoxy. Ensure all absorbent tiles are sealed or protected from direct contact with the epoxy grout as they may stain, even after cleaned off well. Allow 24 hours before light traffic.

Equipment Care

All tools should be cleaned with water immediately after use. If delayed, equipment will need thinners or mechanical action to clean or be discarded.

Packing

Supplied in 1LT Resin + Hardener Kits

Quality Assurance

Multi Construction Chemicals South Africa (PTY) Ltd production and testing programs comply with all local and international testing standards.

REVISION: 3.1